

Elementis Specialties, Inc.	Elementis GmbH
P.O. Box 700, Wyckoffs Mill Rd.	Technical Centre
Hightstown, NJ 08520	Stolberger Strasse 370
Tel.: +1-609-443 2500	50933 Cologne, Germany
Fax: +1-609-443 2422	Tel: +49 (0)221 2923 2000
specialinfo.usa@elementis-na.com	Fax: +49 (0)221 2923 2010
Web: www.elementis-specialties.com	specialinfo.eu@elementis-eu.com



LIPBALM

KR9/132

Lipbalm containing FANCOR® ABYSSINIAN OIL, MEADOWESTOLIDE®, Anti-Aging Skin Complex™ and BENTONE GEL® ABO V.

Advantages

The presence of FANCOR® ABYSSINIAN OIL, MEADOWESTOLIDE®, Anti-Aging Skin Complex™ and BENTONE GEL® ABO V in this system:

- Aide smooth application
- Stabilize the pigments
- Soften the lips

Ingredient	Supplier	% w/w
PHASE A		
FANCOR® ABYSSINIAN OIL (Crambe Abyssinica Seed Oil)	ELEMENTIS Specialties	10.5
BENTONE GEL® ABO V (Crambe Abyssinica Seed Oil, Disteardimonium Hectorite and Propylene Carbonate)	ELEMENTIS Specialties	10.0
MEADOWESTOLIDE® (Meadowfoam Estolide)	ELEMENTIS Specialties	6.0
Anti-Aging Skin Complex™ (Meadowfoam Estolide, Meadowfoam Delta-Lactone, Crambe Abyssinica Seed Oil, Carthamus Tinctorius (Safflower) Seed Oil, Olive Oil Unsaponifiable, Beta-Sitosterol)	ELEMENTIS Specialties	5.0
Prisorine 3631 (Pentaerythrityl Tetraistearate)	Croda	26.21
Beeswax	A&E Connock	14.0
Cromollient DP3A (Di-PPG-3 Myristyl Ether Adipate)	Croda	11.5
Super Sterol Ester (C ₁₀₋₃₀ Cholesterol/Lanostearol Esters)	Croda	6.25
Microcrystalline Wax	Strahl & Pitsch	3.0
Ozokerite Wax (Ozokerite)	Strahl & Pitsch	3.0
Carnauba Wax (Copernicia Cerifera (Carnauba) Wax)	Strahl & Pitsch	2.0
PHASE B		
Chione Snowfall White S130D (Synthetic Fluorophlogopite, Titanium Dioxide)	BASF	1.0
Flamenco Summit Red R30D (Mica, Titanium Dioxide)	BASF	0.5
Flamenco Super Orange 330Z (Mica, Titanium Dioxide)	BASF	0.5
Red 6 Lake		0.054

Method of Manufacture

1. Heat Phase A to 80°C.
2. Add Phase B to Phase A and mix until uniform.
3. Cool to 75°C and package.

N.B.

Please refer to the Product Data Sheets for additional advice on incorporation.

SPECIFICATION:

Appearance: Pale Pink Semi-Solid

The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchases will be subject to a separate agreement which will not incorporate this document.