

Elementis Specialties, Inc.
P.O. Box 700, Wyckoffs Mill Rd.
Hightstown, NJ 08520
Tel.: +1-609-443 2500
Fax: +1-609-443 2422
specialinfo.usa@elementis-na.com
Web: www.elementis-specialties.com

Elementis Specialties
PEGASUSPARK
De Kleetlaan 12 a, bus 3
1831 Diegem, Belgium
Tel.: +32-2-790 76 00
Fax: +32-2-790 76 60
specialinfo.eu@elementis-eu.com



LIPGLOSS WITH BENTONE GEL® PTIS V AND THIXCIN® R

REF- KR9/098

Clear lipgloss containing BENTONE GEL® PTIS V and THIXCIN® R, rheological additives

Advantages

The presence of BENTONE® PTIS V, rheological additive in this system:

- Increases viscosity and emollience
-

Ingredient	Supplier	% w/w
PART A		
BENTONE GEL® PTIS V (Pentaerythrityl Tetraisoostearate and Distearidimonium Hectorite and Propylene Carbonate)	ELEMENTIS Specialties	10.0
Rewopal PIB 1000 (Polyisobutene)	Evonik Degussa	30.0
Castor Oil		25.0
Vivanolin L-101 (Lanolin Alcohol and Mineral Oil)	Amerchol	22.8
Cerabeil Blanchie DAB (Cera Alba)	Barlocher France	8.0
Candellila Wax		3.0
Propylparaben		0.2
PART B		
THIXCIN® R (Trihydroxystearin)	ELEMENTIS Specialties	1.0

Procedure

1. Combine Part A and heat with mixing to 70-75°C.
2. Homogenise and cool to 55°C.
3. Add Part B and mix with high shear for 20 minutes.
4. Cool with propeller stirring to 30°C.

N.B.

Please refer to the Product Data Sheets for additional advice on incorporation.

The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchases will be subject to a separate agreement which will not incorporate this document.