

# SMOOTH GLIDE LIPSTICK WITH BENTONE GEL® CAO V AND BENTONE GEL® PTM V

## REF- S. BLACK 2463

Smooth Glide Lipstick containing BENTONE GEL® CAO V, and BENTONE GEL® PTM V, rheological additives.

### Advantages

The presence of BENTONE GEL® CAO V and BENTONE GEL® PTM V, rheological additives in this system:

- Improves stick stability and aids colour distribution in the product
- Imparts viscosity and body, providing ease of application and spreadability

Ingredient	Supplier	% w/w
<b>PHASE A</b>		
<b>BENTONE GEL® CAO V (Ricinus Communis and Stearalkonium Hectorite and Propylene Carbonate)</b>	<b>ELEMENTIS Specialties</b>	<b>5.0</b>
<b>BENTONE GEL® PTM V (Phenyl Trimethicone and Distearidimonium Hectorite and Triethyl Citrate)</b>	<b>ELEMENTIS Specialties</b>	<b>5.0</b>
Castor Oil (Ricinus Communis)	John L. Seatons	31.15
Trivent OC-G (Tricaprylin)	Trivent	20.0
Cerilla G (Candelilla Cera and Paraffin)	Barlocher	9.0
Softisan 100 (Hydrogenated Coco-Glycerides)	Sasol	8.0
Softisan 645 (Bis-Diglyceryl Polyacyladipate-1)	Sasol	8.0
Cerabeil White (Cera Alba)	Barlocher	3.0
Ceruba T1 (Cera Carnauba)	Barlocher	2.0
Tocopheryl Acetate	Protameen	0.5
Paratexin P (Propylparaben)	S. Black Group	0.1
BHT	Merck	0.05
<b>PHASE B</b>		
COD 8006 (Ricinus Communis and C.I. 77491 and BHT)	Sun Chemical	5.0
Timiron Sun Gold Sparkle MP-29 (Mica and C.I. 77891 and C.I. 77491)	Merck	2.0
COD 8008 (Ricinus Communis and C.I. 77891 and BHT)	Sun Chemical	1.0
COD 8004 (Ricinus Communis and C.I. 77499 and BHT)	Sun Chemical	0.2

---

## Method of Manufacture

1. Heat Phase A together to 85°C.
2. Add Phase B and mix.
3. Pour and cool.

N.B.

Please refer to the Product Data Sheets for additional advice on incorporation.

---

The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchases will be subject to a separate agreement which will not incorporate this document.