

**Elementis Specialties, Inc.**  
P.O. Box 700, Wyckoffs Mill Rd.  
Hightstown, NJ 08520  
Tel.: +1-609-443 2500  
Fax: +1-609-443 2422  
specialinfo.usa@elementis-na.com  
Web: www.elementis-specialties.com

**Elementis Specialties**  
PEGASUSPARK  
De Kleetlaan 12 a, bus 3  
1831 Diegem, Belgium  
Tel.: +32-2-790 76 00  
Fax: +32-2-790 76 60  
specialinfo.eu@elementis-eu.com



# **SOUFFLE LIPGLOSS WITH BENTONE GEL® CAO V AND THIXCIN® R**

**S. Black: 951**

**KR5/094**

Souffle Lipgloss containing BENTONE GEL® CAO V, rheological additive, and THIXCIN® R, rheological additive.

## **Advantages**

The presence of BENTONE GEL® CAO V, rheological additive in this system:

- Delivers a base viscosity
- Provides thermostable viscosity control
- Enhances skin feel

The presence of THIXCIN® R, rheological additive in this system:

- Increases firmness
- Improves stability

<b>Ingredient</b>	<b>Supplier</b>	<b>% w/w</b>
<b>PHASE A</b>		
<b>BENTONE GEL® CAO V (Ricinus Communis and Stearalkonium Hectorite and Propylene Carbonate)</b>	<b>ELEMENTIS Specialties</b>	<b>70.0</b>
Trivent OL-10B (Isodecyl Oleate)	Trivent Chemical Company	17.20
Paratexin P (Propylparaben)	S. Black Group	0.1
<b>PHASE B</b>		
<b>THIXCIN® R (Trihydroxystearin)</b>	<b>ELEMENTIS Specialties</b>	<b>7.0</b>
<b>PHASE C</b>		
Timiron Gleamer Flake MP-45 (Mica and C.I. 77891 and Dimethicone)	Merck	5.0
COD 8002 (Ricinus Communis and C.I. 15850 and BHT)	Sun Chemical	0.4
BHT	Merck	0.1
<b>PHASE D</b>		
Fragrance		0.2

---

## Method of Manufacture

1. Heat Phase A together until melted.
2. Add Phase B and mix.
3. Add Phase C and cool to 50°C.
4. Add Phase D and propeller stir.

N.B.

Please refer to the Product Data Sheets for additional advice on incorporation.

---

The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchases will be subject to a separate agreement which will not incorporate this document.