Elementis Specialties, Inc.

P.O. Box 700, Wyckoffs Mill Rd. Hightstown, NJ 08520

Tel.: +1-609-443 2500 Fax: +1-609-443 2422

specialinfo.usa@elementis-na.com Web: www.elementis-specialties.com

Elementis Specialties

PEGASUSPARK
De Kleetlaan 12 a, bus 3
1831 Diegem, Belgium

Tel.: +32-2-790 76 00 Fax: +32-2-790 76 60

specialinfo.eu@elementis-eu.com



WATER IN OIL INORGANIC SUNCREAM WITH BENTONE GEL® TN V AND NANOX™ 200 RECF- KR8/105

Water in Oil Inorganic Suncream containing BENTONE GEL® TN V, rheological additive, and NANOX™ 200, Ultrafine Zinc Oxide.

Advantages

The presence of BENTONE GEL® TN V, rheological additive, in this system:

- · Gives body, yet allows easy spreading, due to the thixotropic nature
- Promotes even distribution
- Produces a stable emulsion at increased temperatures
- Reinforces emulsion stability, and improves storage stability
- Enhances SPF to an in-vitro SPF of 23.32 +/- 6.47

Ingredient	Supplier	% w/w
PHASE A		
BENTONE GEL® TN V (C ₁₂₋₁₅ Alky Benzoate and Stearalkonium Hectorite and Propylene Carbonate)	ELEMENTIS Specialties	8.0
Tegosoft OS (Ethylhexyl Stearate)	Evonik Degussa	13.5
Isohexadecane	Bayer	8.0
Tegosoft M (Isopropyl Myristate)	Evonik Degussa	5.0
Abil EM 90 (Cetyl PEG/PPG-10-1 Dimethicone)	Evonik Degussa	1.8
Isolan GO 33 (Polyglyceryl 3-Oleate)	Evonik Degussa	1.75
PHASE B		
NANOX™ 200 (Zinc Oxide)	ELEMENTIS Specialties	13.5
T805 (Titanium Dioxide)	Evonik Degussa	2.35
PHASE C		
De-ionised Water		41.4
Magnesium Sulphate Heptahydrate		0.75
Sodium Chloride		0.75
PHASE D		1
1,3-Butylene Glycol	Siber Hegner	3.0
Phenoxetol (Phenoxyethanol)	Clariant	0.2

Method of Manufacture

1. Theat I have A together to 75 O.	1.	Heat Phase A together to 75°C.	
-------------------------------------	----	--------------------------------	--

- 2. Transfer to a Silverson homogeniser, and with mixing gradually add Phase B. Mix until fully dispersed.
- 3. In a separate container warm Phase C to 75°C.
- 4. Using high shear mixing (e.g. Silverson homogeniser), slowly add Phase C to Phase A + B.
- 5. Continue to mix for several minutes.
- 6. Transfer to propeller stirrer and commence cooling.
- 7. Under 35°C add Phase D.
- 8. Mix until uniform.

N.B.

Please refer to the Product Data Sheets for additional advice on incorporation.

The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchases will be subject to a separate agreement which will not incorporate this document.